



Technical Data Sheet (TDS)  
Declaration of Performance  
№ 2259

COD: CC-PF-001  
EDITIA: 1  
REVIZIA: 0  
DATA: 15.01.2020.

1 DATE: 23.10.2020  
2 PRODUCT NAME: Fiberglass mesh: 110 g 10x10  
3 PRODUCTION DATE: 23.11.2020  
4 STORAGE TERM: 2 years after date of production in dry Warehouse

| No | Indicator                                  | Measure | Norm               | Test result | Test Method                        |
|----|--|---------|--------------------|-------------|------------------------------------|
| 1  | Number of threads 10 cm (warp)             | 10 cm   | 9-12               | 11          | EAD 040016-00-0404:2016, Cl. 2.2.6 |
| 2  | Number of threads 10 cm (weft)             | 10 cm   | 9-12               | 11          | EAD 040016-00-0404:2016, Cl. 2.2.6 |
| 3  | Width                                      | cm      | 99,5-101           | 99,9        | EAD 040016-00-0404:2016, Cl. 2.2.5 |
| 4  | Mass per unit                              | gr/m2   | 105-115            | 108         | EAD 040016-00-0404:2016, Cl. 2.2.8 |
| 5  | Ash content                                | %       | Not less than 8    | 23,8        | EAD 040016-00-0404:2016, Cl. 2.2.2 |
| 6  | Tearing Force (warp)                       | N/ 5 cm | Not less than 1200 | 1 350       | u\o 040016-00-0404:2016, Cl. 2.2.7 |
| 7  | Tearing Force (weft)                       | N/5 cm  | Not less than 1800 | 1 554       | u\o 040016-00-0404:2016, Cl. 2.2.7 |
| 8  | Tearing Force after 28 days storage (warp) | N/50 mm | Not less than 600  | 750         | u\o 040016-00-0404:2016, Cl. 2.2.7 |
| 9  | Tearing Force after 28 days storage (weft) | N/50 mm | Not less than 900  | 1 110       | u\o 040016-00-0404:2016, Cl. 2.2.7 |
| 10 | Cell size warp direction                   | mm      | Not less than 10   | 10,0        | EAD 040016-00-0404:2016, Cl. 2.2.4 |
| 11 | Cell size weft direction                   | mm      | Not less than 10   | 10,0        | EAD 040016-00-0404:2016, Cl. 2.2.4 |

Production Director

