



Technical Data Sheet (TDS)  
Declaration of Performance  
№ 2264

COD: CC-PF-001  
EDITIA: 1  
REVIZIA: 0  
DATA: 15.01.2020.

- 1 DATE: 02.06.2021  
2 PRODUCT NAME: Fiberglass mesh 110  
3 PRODUCTION DATE: 01.06.2021  
4 STORAGE TERM: 2 years after date of production in dry Warehouse

No	Indicator	Measure	Norm	Test result	Test Method
1	Number of threads 10 cm (warp)	10 cm	38-42	41	EAD 040016-00-0404:2016, Cl. 2.2.6
2	Number of threads 10 cm (weft)	10 cm	15-19	19	EAD 040016-00-0404:2016, Cl. 2.2.6
3	Width	cm	99,5-101	100	EAD 040016-00-0404:2016, Cl. 2.2.5
4	Mass per unit	gr/m2	105-115	108,5	EAD 040016-00-0404:2016, Cl. 2.2.8
5	Ash content	%	Not less than 10	10,8	EAD 040016-00-0404:2016, Cl. 2.2.2
6	Tearing Force (warp)	N/ 5 cm	Not less than 1000	1 708	u\o 040016-00-0404:2016, Cl. 2.2.7
7	Tearing Force (weft)	N/5 cm	Not less than 1000	2 626	u\o 040016-00-0404:2016, Cl. 2.2.7
8	Tearing Force after 28 days storage (warp)	N/50 mm	Not less than 500	854	u\o 040016-00-0404:2016, Cl. 2.2.7
9	Tearing Force after 28 days storage (weft)	N/50 mm	Not less than 500	750	u\o 040016-00-0404:2016, Cl. 2.2.7
10	Cell size warp direction	mm	Not less than 3	4,9	EAD 040016-00-0404:2016, Cl. 2.2.4
11	Cell size weft direction	mm	Not less than 3	5,3	EAD 040016-00-0404:2016, Cl. 2.2.4

Production Director \_\_\_\_\_

