



Technical Data Sheet (TDS)  
Declaration of Performance  
№ 2264

COD: CC-PF-001  
EDITIA: 1  
REVIZIA: 0  
DATA: 15.01.2020.

1 DATE: 11.12.2020  
2 PRODUCT NAME: Fiberglass mesh 125  
3 PRODUCTION DATE: 24.11.2020  
4 STORAGE TERM: 2 years after date of production in dry Warehouse

Nº	Indicator	Measure	Norm	Test result	Test Method
1	Number of threads 10 cm (warp)	10 cm	20-21	20	EAD 040016-00-0404:2016, Cl. 2.2.6
2	Number of threads 10 cm (weft)	10 cm	15-18	17	EAD 040016-00-0404:2016, Cl. 2.2.6
3	Width	cm	99,5-101	99,9	EAD 040016-00-0404:2016, Cl. 2.2.5
4	Mass per unit	gr/m <sup>2</sup>	125-152	135,8	EAD 040016-00-0404:2016, Cl. 2.2.8
5	Ash content	%	Not less than 11	12,4	EAD 040016-00-0404:2016, Cl. 2.2.2
6	Tearing Force (warp)	N/5 cm	Not less than 1200	1 714	u\o 040016-00-0404:2016, Cl. 2.2.7
7	Tearing Force (weft)	N/5 cm	Not less than 1200	1 552	u\o 040016-00-0404:2016, Cl. 2.2.7
8	Tearing Force after 28 days storage (warp)	N/50 mm	Not less than 1 000	902	u\o 040016-00-0404:2016, Cl. 2.2.7
9	Tearing Force after 28 days storage (weft)	N/50 mm	Not less than 1 000	764	u\o 040016-00-0404:2016, Cl. 2.2.7
10	Cell size warp direction	mm	Not less than 3	5,0	EAD 040016-00-0404:2016, Cl. 2.2.4
11	Cell size weft direction	mm	Not less than 3	5,45	EAD 040016-00-0404:2016, Cl. 2.2.4

Production Director

